

ENGINEER PLUS



PAINTING SOLUTIONS



Ultralite

PREMIUM ENAMEL SATIN

www.sadeeworld.com

Ultralite

PREMIUM ENAMEL SATIN

DIRECTIONS FOR USE

- CLEANING** : Sand the surface with Pure Care Star sanding paper 180 to remove loose particles, paint, dust/grease and cracked or flaked paint. Wipe clean.
- PRIMER** : Apply a first coat of primer depending on the surface.
For wooden surfaces, use Sadee World Pure Care Wood Primer.
For mild steel surfaces, use Sadee World Pure Care Yellow Metal Primer or Sadee World Pure Care Red Oxide Metal Primer.
For wall surfaces, use Sadee World Pure Care Interior Wall Primer ST.
For aluminum and galvanized iron surfaces, use Pure Care Yellow Metal Primer or Etch Primer. Allow drying for 6–8 hours.
- PUTTY** : Smoothen the surface by filling dents with thin coats of putty.
For walls & wooden surfaces, use Sadee World Pure Care Acrylic Wall Putty.
For metal surfaces, use Sadee World Pure Care Knifing Paste Filler.
Allow drying for 6–8 hours. Sand with Pure Care sanding paper 180 & wipe clean.
- PRIMER** : Apply another coat of primer and allow drying for 6–8 hours.
Sand with Pure Care sanding paper 320 and wipe clean.
- TOPCOAT** : Thin a litre of Ultralite Premium Satin Enamel with 80–100 ml of Sadee World WoodTech General Purpose Thinner. Apply 2 coats with an interval of 8 hours between successive coats.

Complies to American Standard ASTM C 494

Global Database D-U-11-S
© No. : 91-624-3785
D&B
Dun & Bradstreet Corporation, USA

ISO
ISO 9001:2018 Certified Company



PRECAUTIONS : While storing used paint, ensure that the container is tightly closed to prevent skin/film formation. Do not keep the material open for a long time. Do not over-thin the material. Shake the material well before use. Mechanically good stir to make the material uniform and homogeneous through a fine sieve before use. Ensure ventilation is maintained during and post application.

PAINTING SYSTEM : 2 coats of PureCare Yellow Metal PU Primer + 2 coats of Ultralite Premium Enamel Satin (for mild steel).

Batch No. : 09

Mfg. Date : Sep. 2025

USP :

MRP : Rs. (Incl. of all taxes)

Company Reg. No. : U70200MP2023PTC065149

® Registered Trademark

Chloride contents - 0.05% max.
Weight & Measure
DCLM/INDORE/502/P/2024



Manufacturer Of World Class Construction Chemicals & Paints :
Sadee World Pvt. Ltd.
Survey No. 157/2, Halka No. 7, Gram Sinhasa, Dhar Road-453001
Customer Care No. : +91 9229182999,
E-mail : sadeeworldsales@gmail.com, sadeeworld99@gmail.com
website : www.sadeeworld.com

4 Ltr.
Net.

For Feedback /Complaints Write to Marketing Manager, Services at
61, Jawahar Marg, Udyog Parisar (Indore) M.P.-India-452007

Customer Care :
+91 92291 82999

